AMENDMENTS TO THE CLAIMS

- 1. (Currently Amended) A silicone coating composition comprising consisting essentially of as essential components,
- (A-1) 100 parts by weight of an organopolysiloxane having at least two alkenyl groups each directly attached to a silicon atom in a molecule, represented by the average compositional formula (i):

$$R^{1}_{a}R^{2}_{b}SiO_{(4-a-b)/2}$$
 (i)

wherein R^1 is independently a substituted or unsubstituted monovalent hydrocarbon group exclusive of alkenyl groups, R^2 is an alkenyl group, a and b are numbers: $0 \le a \le 3$, $0 < b \le 3$ and $1 \le a+b \le 3$,

(B-1) an organohydrogenpolysiloxane having at least three hydrogen atoms each directly attached to a silicon atom (i.e., SiH groups) in a molecule, represented by the average compositional formula (ii):

$$R^{1}_{c}H_{d}SiO_{(4-c-d)/2}$$
 (ii)

wherein R^1 is as defined above, c and d are numbers: $0 \le c \le 3$, $0 < d \le 3$ and $1 \le c+d \le 3$, in such an amount that the moles of silicon-

bonded hydrogen atoms is 1 to 5 times the moles of alkenyl groups in component (A-1),

- (C) 5 to 150 parts by weight of a silicone rubber fine powder having an average particle size of 0.5 to 20 $\mu m,$ and
 - (D-1) a catalytic amount of an addition reaction catalyst.
- 2. (Original) A silicone coating composition comprising as essential components,
- (A-2) 100 parts by weight of an organopolysiloxane having at least two silanol groups in a molecule, represented by the average compositional formula (iii):

$$R^{1}_{e}(OH)_{f}SiO_{(4-e-f)/2}$$
 (iii)

wherein R^1 is independently a substituted or unsubstituted monovalent hydrocarbon group exclusive of alkenyl group, e and f are numbers: $0 \le e \le 3$, $0 < f \le 3$ and $1 \le e + f \le 3$,

(B-2) an organohydrogenpolysiloxane having at least three hydrogen atoms each directly attached to a silicon atom (i.e., SiH groups) in a molecule, represented by the average compositional formula (ii):

$$R^{1}_{c}H_{d}SiO_{(4-c-d)/2}$$
 (ii)

wherein R^1 is as defined above, c and d are numbers: $0 \le c \le 3$, $0 < d \le 3$ and $1 \le c+d \le 3$, in such an amount that the moles of siliconbonded hydrogen atoms is 5 to 200 times the moles of silanol groups in component (A-2), or

an organopolysiloxane having at least three hydrolyzable groups each directly attached to a silicon atom in a molecule, represented by the average compositional formula (iv):

$$R^{1}_{g}R^{3}_{h}SiO_{(4-g-h)/2} \qquad (iv)$$

wherein R^1 is as defined above, R^3 is a hydrolyzable group, g and h are numbers: $0 \le g \le 3$, $0 < h \le 3$ and $1 \le g+h \le 3$, in such an amount that the moles of hydrolyzable groups is 5 to 200 times the moles of silanol groups in component (A-2),

- (C) 5 to 150 parts by weight of a silicone rubber fine powder having an average particle size of 0.5 to 20 $\mu m\text{,}$ and
 - (D-2) a catalytic amount of a condensation reaction catalyst.
- 3. (Currently Amended) The A silicone coating composition of claim 1 wherein the silicone rubber fine powder (C) has been surface coated with polyorganosilsesquioxane consisting essentially of as essential components,

(A-1) 100 parts by weight of an organopolysiloxane having at least two alkenyl groups each directly attached to a silicon atom in a molecule, represented by the average compositional formula (i):

$$R_{a}^{1}R_{b}^{2}SiO_{(4-a-b)/2}$$
 (i)

wherein R^1 is independently a substituted or unsubstituted monovalent hydrocarbon group exclusive of alkenyl groups, R^2 is an alkenyl group, a and b are numbers: $0 \le a \le 3$, $0 < b \le 3$ and $1 \le a+b \le 3$,

(B-1) an organohydrogenpolysiloxane having at least three hydrogen atoms each directly attached to a silicon atom (i.e., SiH groups) in a molecule, represented by the average compositional formula (ii):

$$R^{1}_{c}H_{d}SiO_{(4-c-d)/2} \qquad (ii)$$

wherein R^1 is as defined above, c and d are numbers: $0 \le c \le 3$, $0 < d \le 3$ and $1 \le c+d \le 3$, in such an amount that the moles of silicon-bonded hydrogen atoms is 1 to 5 times the moles of alkenyl groups in component (A-1),

- (C) 5 to 150 parts by weight of a silicone rubber fine powder having an average particle size of 0.5 to 20 μm and having been surface coated with polyorganosilsesquioxane, and
- (D-1) a catalytic amount of an addition reaction catalyst.
- 4. (Original) A release sheet comprising a cured coating of the silicone composition of claim 1.
- 5. (New) The silicone coating composition of claim 2 wherein the silicone rubber fine powder (C) has been surface coated with polyorganosilsesquioxane.
- 6. (New) A release sheet comprising a cured coating of the silicone composition of claim 2.
- 7. (New) A release sheet comprising a cured coating of the silicone composition of claim 3.
- 8. (New) The silicone coating composition of claim 2, which consists essentially of the essential components (A-2), (B-2), (C) and (D-2).

9. (New) A method for making a silicone coating composition which consists essentially of mixing together as essential components the components (A-1), (B-1), (C) and (D-1) recited in claim 1.